

RLPP721 ORANGE

RLPP721 Orange is a Polypropylene (PP) Compound specifically developed for rotational lining of metal vessels, valve bodies and pipelines. It has been compounded with an orange pigment to differentiate from other polymers used for lining, in accordance with international standards.

It meets the pass requirements when tested to reference U.S. 21 CFR F.D.A. Regulation Part 177.1520 Clause 3.1a.

RLPP721 has excellent processability and its enhanced properties allow it to be used in demanding applications requiring high levels of ESCR, chemical resistance and operation at continuously high temperatures up to 210⁰ F.

FEATURES:

- **An excellent balance of high stiffness & impact**
- **Good Temperature Resistance (dry & wet)**
- **High FNCT / ESCR and good chemical resistance**
- **Rated > UV12**
- **High elongation at failure.**

PROCESSING GUIDELINES:

- Oven temperature ~ 300°C (570°F) to achieve mold surface temperature > 470°F
- PIAT 420°F
- Rotation similar to LMDPE
- Ensure metal surface is clean, sand blasted and degreased
- If lining stainless steel, a primer must be used
- Cool evenly and slowly to optimize mechanical properties

OBSERVATIONS:

- Lower shrinkage than PE

TYPICAL APPLICATIONS:

- Chemical tanks, fittings, flanges, pipes
- Protection against corrosion

Properties	Conditions	Units	Nominal Values	Testing Methods
Physical				
Melt Flow Rate	230°C/2.16kgs	g/10 min	14	ASTM D1238
Density ²		g/cm ³	0.900	ASTM D792
Mechanical & Thermal				
Tensile stress ¹	At yield	PSI	3190	ASTM D638
Tensile strain ¹	% At yield % At break	% %	5 >300	ASTM D638
Tensile Modulus ¹		PSI	159000	ASTM D638
Flexural Modulus ¹		PSI	159000	ASTM D790
FNCT ² 2% Ige *	5MPa @ 50°C 6MPa @ 50°C	Hours Hours	>300 170	ASTM D1693
ESCR ¹	2% Igepal *	Hours	> 1000	ASTM D1693
Shore D Hardness ¹			62	ASTM D2240
HDT ¹ HDT ¹	264 PSI 66 PSI	Deg F Deg F	239 143	ASTM D648
Poisson Ratio			0.44	ASTM E132

Notes: ¹ Roto molded

² Compression molded

* Or equivalent

Bonding to steel:

Salee conducted internal testing of 3 roto industry commercially available PE grades, one of which can be considered the best available, alongside **FRLPP721 Orange** according to ASTM D3167 “Floating Roller Peel Resistance of Adhesives”.

Conditions:

Mechanical properties test (Tensile) by Universal Testing Machine

Model: LLOYD LR10K

Sample size: SPECIMEN (ASTM D3167)

Load cell: 10KN

Test speed: 152 mm/min

Test Type: Peel (90° & 180°)

Samples were tested with a ‘sand blasted’ surface as well as a solvent wash only.

RLPP721 Orange exhibited excellent bond strength under all conditions, no peeling of the polymer from the metal was observed. The best commercial PE yielded similar results.

Important: *The information contained in this document is of a general nature only and is intended to provide an indication of the potential properties and benefits of a particular polypropylene compound. The statistical and other information provided in this document has been determined in laboratory test conditions. Accordingly, there may be differences in performance in a production environment including having regard to the materials used. The information contained in this document should not be used as a sole basis for production or manufacturing purposes. Independent testing verification and independent professional advice should be obtained before making a decision to use any product or to apply any method or process. To the full extent permitted by law, Salee Colour Public Company Limited (Salee Colour) its related entities, their directors /employees: & sales company PSD Rotoworx P/L, (i) give no warranty or representation that the information contained in this document is accurate and complete in every particular, and (ii) disclaim all liability for reliance on the information contained in this document.*

**Salee Colour Public Company Limited,
858 Moo 2, Soi 1C/1,
Bangpu Industrial Estate,
Bangpumai, Muang Samutprakarn
Samutprakarn 10280, Thailand
Contact: sales@psdrotoworx.com**